


SiSiB[®] HF2030-M134

1,1,3,3-Tetramethyldisiloxane

CHEMICAL NAME

1,1,3,3-Tetramethyldisiloxane, TMDS, TMDSO

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] HF2030-M134 fluid is a colorless to yellowish clear liquid.

TYPICAL PHYSICAL PROPERTIES

CAS No.	3277-26-7
EINECS No.	221-906-4
Formula	C ₄ H ₁₄ OSi ₂
Molecular Weight	134.33
Boiling Point	70°C [760mmHg]
Flash Point	-12°C
Color and Appearance	Colorless transparent liquid
Density _{25/25°C}	0.757
Refractive Index	1.3669 [20°C]
Hydrogen Content wt%	1.49%
SiH Content	14.9mmol/g
Active content:	Min.99.0%

APPLICATIONS

SiSiB[®] HF2030-M134 is used in for Plasma Enhanced Chemical Vapor Deposition (PECVD) of glass on a variety of substrates at low temperature.

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

SiSiB[®] HF2030-M134

1,1,3,3-Tetramethyldisiloxane

SiSiB[®] HF2030-M134 is also employed in reductive halogenation of aldehydes and epoxides.

SiSiB[®] HF2030-M134 is used as starting material for the production of hydride terminated polydimethylsiloxane.

PACKING AND STORAGE

SiSiB[®] HF2030-M134 is supplied in 20Kg or 130Kg steel drum.

In the unopened original container SiSiB[®] HF2030-M134 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.